

Certificate of Analysis

Shea Clark Smith /MEG, Inc.

Minerals Exploration & Environmental Geochemistry

P.O. Box 18325 Reno, Nevada, U.S.A. 89511-0325

Email: SheaClarkSmith@aol.com Website: SheaClarkSmith.com

Tel: 775-849-2235

MEG-Au.13.03

Certified Reference Material

MEAN = 1.823 ppm Au

95% Confidence = 1.609 - 2.038

Prepared By: Shea Clark Smith / Minerals Exploration & Environmental Geochemistry

Certified By: Shea Clark Smith, MSc.(Geochemistry)

Manufactured for: MEG LABS

Date of Certification: January 2, 2013

Origin of Reference Material:

Certified Reference Material MEG-Au.13.03 was created from mineralized rock from the Springpole Mine, Ontario, Canada.

This material is not intended to be matrix-matched to any specific ore lithology.

Method of Preparation:

Rock from the Springpole Mine (with a natural concentration of 1.8 ppm Au and 4.5 ppm Ag) was dried at 100C, jaw crushed, and roll crushed to -400 um.

The batch was comminuted to powder in a ceramic ball mill for 150 hours.

Sizing tests of the final product show greater than 93% pass -74um (-200 mesh).

The standard was packaged in 50 g envelopes, each envelope with a removable sticky-label.

Method of Analysis:

Using the ICPMS capabilities of just one laboratory, homogeneity tests were done to estimate multielement distributions from a 4-acid digestion (0.5 gram) from each of 10 samples.

Then, 5 samples each to 10 laboratories were fire assayed on 30 gram subsamples with AAS finish, and these data were used to certify the material for gold concentration.

Summarized Assay Results:

PROJECT: MEG-Au.13.03 reported in ppm (parts per million)

DATA POINTS (ALL DATA)	57
MEAN (ALL DATA)	1.823
STANDARD DEVIATION (ALL DATA)	0.119
% RSD	6.51
RANGE OF VALUES - HIGH	2.072
RANGE OF VALUES - LOW	1.529
95% CONFIDENCE LIMITS	1.586 to 2.061

DATA POINTS (LAB AVERAGE DATA)	10
MEAN (LABS)	1.823
STANDARD DEVIATION (LABS)	0.107
CV (% RSD)	5.89
RANGE OF VALUES - HIGH	2.019
RANGE OF VALUES - LOW	1.626
95% CONFIDENCE LIMITS	1.609 to 2.038

Statistical Procedures:

Acceptable assay limits are based on the results of 5 samples shipped to each of 10 laboratories.

The samples were submitted with other MEG standards in randomized order, so that as much as possible, real operating conditions were obtained from the participating laboratories. All of the data were used to determine an acceptable range, based on the mean and standard deviation of the "Lab Average Data". The acceptable reporting range is the "95% Confidence Limit", which is the mean +/- 2 standard deviations. Other statistics are provided to help the user assign viable acceptance boundaries.

Standards with an RSD (Relative Standard Deviation) of near or less than 5% are termed "Certified", while RSD's between 5% to 15% are designated "Provisional". RSD's over 15% are "Informational".

Instructions and Recommendations for Use:

Submit the entire contents of one 50 g envelope in random locations in the submittal, approximately every 10-20 samples. Use of blanks (samples with "below detection" concentration of analyte) are also recommended, randomly placed every 30-40 samples. The analytical request should be the same as that used for the round robin assays that generated this certificate.

Intended Use:

The standard material can be used to validate the analysis of samples from gold ores with a similar grade.

As a control sample in routine assay laboratory operations, it should behave within the limits as indicated statistically in this certification. Its intended use is to monitor inter-laboratory and instrumental bias within these limits.

The recommended concentrations and limits for this material are based on multiple assays from several laboratories and reflect a consensus of the inherent chemical concentration. These values are a first attempt at a chemical characterization to which later data may be added as experience with the material increases.

Slight variations in analytical procedures between laboratories will result in slight biases to the recommended statistical limits.

This standard material is not recommended for method development, nor instrumental calibration.

Handling Instructions:

The material is packaged in manila tin-top envelopes for easy open and close use. The material should be reblended just prior to use in the assay laboratory. This can be done with a micro-riffle splitter or rubber sheeting. Simple agitation and shaking is not sufficient to rehomogenize prior to use.

Normal safety precautions for handling powders are recommended. The use of safety glasses, dust inhalation protection, gloves, and a laboratory coat are suggested.

Safety Notice:

A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Use regular precautions as for any work with fine powder material.

Legal Notice:

This certificate and the referenced material have been prepared with due care and attention. However, Minerals Exploration & Environmental Geochemistry (MEG Labs), and Shea Clark Smith, MSc, P.G., accept no liability for any decisions or actions taken following the use of this geochemical reference material.

Assay Data Used to Calculate "True" Gold Value:

Sample	Lab 1 ppm Au	Lab 2 ppm Au	Lab 3 ppm Au	Lab 4 ppm Au	Lab 5 ppm Au	Lab 6 ppm Au	Lab 7 ppm Au	Lab 8 ppm Au	Lab 9 ppm Au	Lab 10 ppm Au
1	1.840	2.072	1.59	1.8	1.86	1.563	1.812	1.96	1.9	1.8
2	1.810	1.994	1.63	1.8	1.9	1.529	1.833	1.89	1.909	1.79
3	1.840	2.019	1.66	1.9	1.87	1.943	1.773	1.81	1.974	1.77
4	1.900	2.016	1.64	1.79	1.82	1.683	1.763	1.88	1.875	1.74
5	1.800	2.012	1.61	1.805	1.8	1.884	1.676	1.88	1.967	1.79
6		1.999		1.81		1.85				
7				1.795						
8				1.765						
9				1.765						
10				1.78						
11										


Major Constituents as Oxides

Average of 10 samples: 4-ACID, ICPMS (Total Digestion)

Raw Data:	Al%	Ca%	Fe%	K%	Mg%	Na%	S%	Ti%	Si%
ICP/MS Data (n=10)	7.98	0.21	9.40	5.20	0.82	0.08	0.51	0.10	
Conversion Factor	1.8899	1.3992	1.4297	1.2046	1.6579	1.348	2.4953	1.6681	2.1392
	Al₂O₃	CaO	Fe₂O₃	K₂O	MgO	Na₂O	SO₃	TiO₂	SiO₂ estimated
% Oxide:	15.09	0.29	13.44	6.27	1.36	0.11	1.27	0.16	62.01

Participating Laboratories:

AMERICAN ASSAY	GENALYSIS
ACME	SKYLINE
ACTIVATION LABS	SGS (LAKEFIELD)
ALS-VANCOUVER	INSPECTORATE (SPARKS)
OMAC (IRELAND)	ULTRATRACE (AUSTRALIA)

Certified By:  _____
 Shea Clark Smith, MSc., P.G.